

# STELLAR 300

## HFC Free Extruded Polystyrene Insulation

### R-VALUE R1.9

R-Values represent the resistance to heat flow. Higher R-Values equal greater insulation performance.

Pieces	Length mm	Width mm	Thickness mm	Lambda ASTM-C518	Compressive Strength k/Pa	Area per Board m <sup>2</sup>	Area per Pack m <sup>2</sup>	Net Kg Weight per Board	Net Kg Weight per Pack
10	2280	600	50	R1.9	300	1.37	13.68	2.2	22

### International Standards

ASTM D1621	GB/T 8811
ASTM C518/ AS-2464.5	GB 8624
ASTM c272	GB/T 10801.1
GB/T 10294	AS 1530.3
GB/T 8810	AS 4859.1*

Fire Grade: B1 (oxygen Index: 27)

Water Absorption: ≤1.0%. We use CO<sub>2</sub> foaming agent

This product should be covered if stored outdoors for extended periods.

For more product information please contact your local representative.

**Warning:** To prevent ignition and smoke, keep away from open flame and high temperature.

Results pending\*



**AUSTECH**

external building products

stellarx.com.au

**CALL 1300 554 922**